

# CONVENTION ON THE CONTROL AND MARKING OF ARTICLES OF PRECIOUS METALS

PMC/W 2/2001 (Rev.12)

Annex

1 December 2025

## COMPILATION OF

### DECISIONS ON TECHNICAL MATTERS RELATED TO ANNEXES I AND II OF THE CONVENTION ON THE CONTROL AND MARKING OF ARTICLES OF PRECIOUS METALS

*Adopted by the Standing Committee on the basis of Article 10,  
paragraph 2, 3<sup>rd</sup> indent, of the Convention (as amended in 2001)  
at its 66<sup>th</sup> meeting in Zurich on 13 April 2010*

*Entered into force on 1 June 2010*

*Last amended on 26 November 2025 with entry into force on 1 December 2025*

© Precious Metals Convention 2025  
Reproduction prohibited for commercial purposes.  
Reproduction for internal use is authorised,  
provided that the source is acknowledged.

Editor: Secretariat of the Precious Metals Convention

e-mail: [info@hallmarkingconvention.org](mailto:info@hallmarkingconvention.org)

web site: <https://www.hallmarkingconvention.org>

## INDEX

	Page
Index .....	2
Note to the Reader .....	3
TECHNICAL DECISIONS REGARDING ANNEX I.....	4
1 Definitions .....	4
2 Technical requirements.....	5
2.1 Articles not covered by the Convention .....	5
2.2 Standards of fineness .....	5
2.3 Tolerance .....	6
2.4 Use of solder .....	6
2.5 Use of working base metal parts and non-metallic substances.....	7
2.6 Multimetall articles .....	9
2.7 Coating of precious metal articles .....	9
TECHNICAL DECISIONS REGARDING ANNEX II.....	11
1 General.....	11
2 Testing .....	12
3 Test methods and methods of analysis .....	13
4 Guidelines on methods of sampling .....	14
4.1 Introduction.....	14
4.2 Screening .....	14
4.3 Sampling.....	15
4.4 Lot consisting of one part or several parts of the same material .....	16
5 Marking.....	17
5.1 Principle.....	17
5.2 Methods of marking.....	17
5.3 Display .....	18
5.4 Register for responsibility marks .....	18
5.5 The Common Control Mark .....	18

5.6	Articles consisting of more than one alloy of the same precious metal .....	18
5.7	Articles consisting of parts .....	18
5.8	Mixed precious metal articles .....	19
5.9	Multimetal articles .....	20
Annex.....		21

---

### **NOTE TO THE READER**

This compilation contains technical requirements for the practical implementation of Annexes I and II of the Precious Metals Convention (document PMC/W 2/2000 (Rev. 3)). Both documents must thus be read in parallel.

In the Convention's Annexes reference is made to specific rules, methods, exceptions, etc., which are defined by the Standing Committee. The present compilation contains such specific rules, methods, exceptions, etc., which have been decided by the Standing Committee on the basis of Article 10, paragraph 2, 3<sup>rd</sup> indent, of the Convention.

The numbering of headings in this compilation follows the same numbering as in the Convention's Annexes.

Examples given at Annex of the present compilation are for illustration purposes only; they are not exhaustive.

# TECHNICAL DECISIONS REGARDING ANNEX I

## *(Definitions and Technical Requirements)*

### **1. DEFINITIONS**

#### **1.1 Precious metals**

-

#### **1.2 Precious metal alloy**

Annex I defines a precious metal alloy as “a solid solution containing at least one precious metal”. By “solution” is meant a mixture of a precious metal with other metallic or non-metallic substances which is homogeneous<sup>1</sup> at least at the macroscopic scale<sup>2</sup>.

#### **1.3 Precious metal article**

-

#### **1.4 Mixed precious metal article**

-

#### **1.5 Multimetal Article**

-

#### **1.6 Fineness**

-

#### **1.7 Standard of fineness**

-

#### **1.8 Coating/plating**

Permitted materials are precious metals (or precious metal alloys) and non-metallic substances.

---

<sup>1</sup> A substance is homogeneous when it shows no variation in properties

<sup>2</sup> i.e. seen or measured by a 10x magnifying glass but without the help of a microscope

## **1.9 Base metals**

-

## **1.10 Assay**

-

## **1.11 Other definitions and further details**

-

# **2. TECHNICAL REQUIREMENTS**

## **2.1 Articles not covered by the Convention**

Ingots are assimilated to bars<sup>3</sup> and thus not considered as articles covered by the Convention.

## **2.2 Standards of fineness applied under the Convention**

### **A. Minimum standards**

The minimum standards of fineness applied under the Convention are the following:

Platinum: 500  
Gold: 375  
Palladium: 500  
Silver: 800

### **B. Nominal standards**

The nominal standards of fineness applied under the Convention are the following:

Gold	375 ‰
	417 ‰
	585 ‰
	750 ‰
	800 ‰
	916 ‰
	990 ‰
	999 ‰

---

<sup>3</sup> Article 2.1, letter e, of Annex 1: “Raw materials such as bars, plates, wire and tubes”.

Platinum	500 ‰ 600 ‰ 850 ‰ 900 ‰ 950 ‰ 990 ‰ 999 ‰
Palladium	500 ‰ 950 ‰ 990 ‰ 999 ‰
Silver	800 ‰ 830 ‰ 835 ‰ 925 ‰ 958 ‰ 990 ‰ 999 ‰

## 2.3 Tolerance

-

## 2.4 Use of solder

2.4.1 -

2.4.2 Practical exceptions and other methods of joining

### A. Practical exceptions

#### A1. Precious metal

##### *Gold*

- Gold alloy articles with a fineness of more than 750/1000 shall be soldered with solder of a minimum fineness of 750/1000 gold.
- In the case of gold articles of filigree work and watch cases of the 750 standard, the solder shall contain not less than 740 parts of gold per 1,000. For white gold articles of the 750 standard the solder shall contain not less than 585 parts of gold per 1,000.

- Gold chains made from wire with less than 1mm diameter can be soldered with solder without gold contents. The solders shall not induce a decrease of the measured mean fineness below the declared fineness.

#### *Silver*

- Solder for silver articles of the 925 standard shall contain not less than 650 parts of silver per 1,000.
- Solder for silver articles of the 800 and 830 standards shall contain not less than 550 parts of silver per 1,000.

#### *Platinum*

- For joining parts of platinum articles solder shall be used with a minimum total content of precious metals<sup>4</sup> of 800 parts per 1,000<sup>5</sup>.

#### *Palladium*

- For joining parts of palladium articles solder shall be used with a minimum total content of precious metals<sup>3</sup> of 700 parts per 1,000<sup>6</sup>.

#### A2. Mixed precious metal

The solder can be the permitted solder for the least precious metal fineness.

#### A3. Precious metal with base metal

Any suitable solder, including base metal, can be used.

#### B. Other methods of joining

Adhesives may be used instead of the permitted solders.

### **2.5 Use of working base metal parts and non-metallic substances in precious metal articles**

#### 2.5.1 -

---

<sup>4</sup> Precious metals are defined at paragraph 1.1 of Annex I to the Convention.

<sup>5</sup> This rule applies to all standards of fineness of platinum, as defined at paragraph 2.2 of Annex I to the Convention.

<sup>6</sup> This rule applies to all standards of fineness of palladium, as defined at paragraph 2.2 of Annex I to the Convention.

## 2.5.2 Further details & exceptions

### A. Further details

#### A1. Base metal parts and non-metallic part for technical reasons

Examples of base metal parts permitted as a mechanical function for which precious metals are unsuitable either for strength or durability are given at Annex.

#### A2. Non-metallic substances

In electroformed articles the kernel made of non-metallic substance (e.g. plastic, wax, etc.), which is needed for the electrochemical manufacturing process of the shell, must be removed after the process. Electroformed articles must be hollow and self-supporting.

#### A3. Mark "METAL"

Marks, which have an equivalent and unequivocal meaning and which are commonly used, are authorised. "Equivalent and unequivocal" means that the alternative term is synonymous to METAL (a similar term or name) and explicit, i.e. not subject to interpretation. Example: "stainless steel". Abbreviations shall not be used with the exception of "MET"<sup>7</sup> for "METAL" due to a lack of space on the item or aesthetic reasons. Subject to B1, chemical symbols of the periodic table can be added.

### B. Exceptions

B1. Where it is impracticable to stamp or engrave "METAL", the base metal part shall be clearly distinguishable by colour from the precious metal with the exception of clock or watch movements. See also A3 and 5.9.

B2. Non visible, non-metallic substances are permitted in the following cases:

- Filling the base with non-metallic material is permitted for better stability (e.g. candle holders, flowerpots and similar silver articles).
- Filling the handles with mastic (or similar material) is allowed (e.g. cutlery, salad servers, carving knives and forks, dessert knives, manicure sets, toilet sets and similar articles).

---

<sup>7</sup> "MET." is also acceptable.

## 2.6 Multimetal Articles

2.6.1 Para. 2.6.1, letter b, of Annex 1 should be understood to mean that base metal parts and non-metallic parts shall be neither coated nor treated to give the appearance of any precious metal used in the item.

### 2.6.2 Further details & exceptions

A multimetal article is an article composed of:

- (1) a precious metal of a standard of fineness applied in this Convention (see paragraph 2.2 of Annex I) having
  - a) a thickness of not less than 500 micrometres,
  - b) a surface sufficiently large to allow the application of the marks defined in paragraph 5.1 of Annex II of the Convention (for marking requirements and minimum size, see paragraphs 5.1.3 and 5.5.2),

and

- (2) non-precious metals, which are:
  - a) visible,
  - b) distinguishable by colour (i.e. neither coated nor treated to give the appearance of a precious metal),
  - c) marked <METAL> (or equivalent<sup>8</sup>) in line with the Convention's requirements (Annex I to the Convention).

## 2.7 Coating of precious metal articles

### A. Permitted coatings

Subject to the provisions of paragraph 5.8.1 of Annex II concerning the differentiation of colours on mixed articles, the following coatings are permitted:

- a) Metallic coating (for example: galvanic) in accordance with the table below:

On	Permitted
Platinum	Rhodium, ruthenium, platinum
Gold	Rhodium, ruthenium, platinum, gold

---

<sup>8</sup> See 2.5.2 A3 above

Palladium	Rhodium, ruthenium, platinum, gold, palladium
Silver	Rhodium, ruthenium, platinum, gold, palladium, silver

The precious metals coatings must reach at least the minimum standards of fineness, as defined in paragraph 2.2A above.

If the alloy and the coating are made of the same precious metal, the coating's standard of fineness must be not less than the alloy's fineness.

- b) Chemical or long-lasting thermal treatments (e.g. sulphured silver, Physical Vapour Deposition [PVD], Chemical Vapour Deposition [CVD])

The colouring of the surface of articles of precious metals by means of chemical transformation of the alloy or its components may be permitted under the terms of the Convention as long as any cross-section of such articles is to a standard of fineness applied under the Convention.

- c) Non metallic coatings (e.g. enamel, niello)

#### B. Exceptions for technical reasons

Coatings (e.g. TiN) combined with a gold top coating on functional and non-visible surfaces of platinum watch components can be accepted for technical reasons.

\* \* \* \* \*

## TECHNICAL DECISIONS REGARDING ANNEX II

### *(Control by the authorised assay office(s))*

#### 1. General

1.1 In line with paragraph 1.1 of Annex II, the term “authorised assay office” is hereinafter referred to as “assay office”.

1.3 The subcontracting of testing is permitted as follows:

##### A. Short-term subcontracting

Subject to paragraph B2.1, letter c, an assay office may subcontract its testing competence to another assay office for a limited period of time normally not exceeding one year due to reasons, which are outside its control, e.g. equipment failure, damages to premises, etc.

##### B. Long-term subcontracting

###### B1. Within a Contracting State

An assay office may subcontract its testing competence to another assay office in the same Contracting State, subject to paragraph B2.1, letter c and the agreement of the Competent Ministry, which shall inform the Standing Committee.

###### B2. Between Contracting States

B2.1. For metal alloys and standards of fineness, which are uncommon or so low in quantity per year that it would not be possible to achieve enough experience and competence, an assay office may subcontract its testing competence to another assay office located in another Contracting State, subject to the following conditions:

- a) The Standing Committee, based on a recommendation of the Standing Technical Group (STG), has given its prior agreement to the subcontracting;
- b) The assay office must provide statistical evidence that the testing competence to be outsourced is not a core competence (see B2);
- c) The assay office, to which the testing competence has been subcontracted, is:
  - accredited to ISO 17025 for the testing method;
  - authorised under Article 5 of the Convention; and
  - has no z-score  $> |3|$  for 2 consecutive Round Robins over the last 5 years.

B2.2. The core competence of an assay office is screening, testing and marking. Testing can be subcontracted if:

- a) it contributes marginally to the entire assay office<sup>9</sup> activity (e.g. less than 5% of the total volume of all articles marked by the assay office);
- b) it is not sufficiently important to justify the purchase and maintenance of specialised equipment; and
- c) it does not allow the staff to maintain its competence.

B3. The guidelines for the assessment requirements of a testing laboratory are contained in the Compilation of Acts of the Standing Committee.

1.4 A non-accredited laboratory should meet at least the following requirements of ISO 17025:

- Developing and implementing Standard Operating Procedures (SOPs) for all relevant methods. The SOPs must be based on the general principles of ISO 17025.
- Using traceable reference material.
- Checking the accuracy of analytical instruments on a regular basis.
- Participating in proficiency testing e.g. Round Robins.
- Defining and implementing a procedure for corrective actions.
- Defining the responsibilities of all relevant laboratory staff.
- Planning and conducting internal quality audits at least once a year.

In order to ensure the correctness and reliability of the analyses and to comply with the requirements of ISO 17025, each of the above steps must be carefully monitored and fully documented. The documentation should be continuously updated and readily accessible on request.

1.5 For the guidelines on Round Robin, see Compilation of Acts of the Standing Committee.

## **2. Testing**

-

---

<sup>9</sup> In Contracting States, which have voluntary hallmarking and where the number of marked articles is low, the activity of the organisation, to which the assay office belongs, shall be considered.

### **3. Test Methods and Methods of Analysis**

3.1 The homogeneity of the batch may be evaluated by one of the following test methods:

- a) touchstone testing;
- b) testing by X-ray spectroscopy;
- c) analysis of scraps assembled from one or more pieces taken out of the batch.

Other test methods may be used to evaluate the homogeneity of the batch.

3.2 The fineness of the precious metals content is determined by one of the following approved methods of analysis:

#### **3.2.1 Platinum:**

ISO 11210, latest version  
ISO 11494, latest version

#### **3.2.2 Gold:**

ISO 11426, latest version

#### **3.2.3 Palladium:**

ISO 11490, latest version  
ISO 11495, latest version

#### **3.2.4 Silver:**

ISO 11427, latest version  
ISO 13756, latest version

#### **3.2.5 For all precious metals:**

X-ray spectrometric method, when the internal method is accredited to ISO 17025 (latest version) and the measurement uncertainty is equal to or better than that of already accepted methods<sup>10</sup>.

---

<sup>10</sup> This means that the measurement uncertainty of the X-Ray spectrometric method should not exceed the following limits:

- gold  $\pm 0.5\text{‰}$
- silver  $\pm 1.0\text{‰}$
- platinum  $\pm 5.2\text{‰}$
- palladium  $\pm 5.8\text{‰}$

## 4. Guidelines on Methods of Sampling

### 4.1 Introduction

The control and marking of articles of precious metals with the CCM consists of (i) assessing the conformity of the precious metal article and (ii) certifying that it is in compliance with the Convention's requirements. This is confirmed by applying the CCM.

The present guidelines relate to the conformity assessment of articles of precious metal. Three distinct steps can be distinguished:

- Screening
- Sampling
- Assaying

### 4.2 Screening

4.2.1 Screening is a qualitative and semi-quantitative testing of an article's material properties and consists of:

- Visual inspection to ascertain that the articles are marked in accordance with the requirements of the Convention.
- Visual inspection to detect any excessive or sub-standard solder.
- Visual inspection to detect base metal parts or unauthorized filling.
- Test for the presence of plating or other coating and determination of its nature by chemical or other methods such as XRF.
- Segregation of any doubtful articles for special tests.

4.2.2 Three different levels of screening are defined based on the quality level of conformity of articles detected over the rolling year. Information data should be maintained for two years minimum. The appropriate level of screening is determined according to the following formula:

$$QL = \left[ 1 - \frac{\sum(\text{articlesrejected})}{\sum(\text{articlessubmitted})} \right] \times 100\%$$

Rejected Article = Articles which do not conform with the material and technical requirements of the Convention.

Note: Such requirements include, for example, fineness, authorised coatings, solder composition, authorised working parts or any other technical requirements.


$\sum$  Articles Rejected = Total sum of articles rejected

Note: If one article of a lot is rejected, all articles of the same lot are rejected.

## ARTICLES ACCEPTED as a % of ARTICLES SUBMITTED

Level 3	0 – 94.9%	Lowest confidence level	Most screening required
Level 2	95 – 98.9%	Normal confidence level	
Level 1	+ 99%	Highest confidence level	Least screening required

4.2.3 Screening should be performed according to the following plan:



## 4.3 Sampling

4.3.1 The following methods of sampling may be used:

- cutting
- scraping
- drilling

4.3.2 Cutting is the preferred method for accuracy but it is often not practicable. In such cases, samples may be removed by scraping. In special circumstances samples may also be obtained by drilling.

4.3.3 In special circumstances when an article would be unreasonably damaged by sampling, it is permissible to carry out the assay on a sample of the material used in its manufacture. In such cases the assay office must take any necessary steps to ascertain that the sample is from the same batch of material as that from which the article is made (i.e. the same coil of wire, sheet, bar, etc.).

4.3.4 If the surface of the article has been enriched (e.g. by pickling) or if it has been coated with a permitted metal (e.g. by electro deposition), the surface layer must

be removed before the sample is taken. This can be carried out by scraping, filing or buffing.

- 4.3.5 Samples may be taken from convenient positions provided that they are representative of the part being sampled. Solder may be included in the sample, except in cases where it is permitted under the terms of the Convention to be of a lower standard of fineness than the standard of the article. Other types of surface impurities such as residues of polishing media must also be removed before samples are taken. Lacquer must also be removed by a suitable solvent.
- 4.3.6 Samples from articles which have been polished or are contaminated with grease may require to be degreased in a suitable solvent before they are assayed.
- 4.3.7 According to paragraph 4 of Annex II to the Convention, the number of articles selected for sampling and the extent to which samples from more than one article are grouped together before assaying will depend on circumstances. For example, in some cases, it may be more appropriate to select one or more articles at random from a lot and to assay them separately, in other cases it may be preferable to sample a greater number of articles and group the samples together before assay. Experience of the likely variation in fineness within a lot and the extent to which the articles may be damaged by sampling will be the deciding factors. In general, there should be a recommended number of articles selected according to the size of the lot and the screening level (see 4.2.3). The following table gives recommended numbers of articles to be selected from lots of different sizes.

#### 4.4 Lot consisting of one part or several parts of the same material

LOT SIZE	SCREENING*			Recommended ASSAYS
	Level 1	Level 2	Level 3	
1	1	1	1	1
2 to 8	2	2	2	1
9 to 15	2	2	3	1
16 to 25	2	3	5	1
26 to 50	2	5	8	1
51 to 90	2	5	13	1
91 to 150	3	8	20	1
151 to 280	5	13	32	1
281 to 500	5	20	50	2
501 to 1,200	8	32	80	2
1,201 to 3,200	13	50	125	3
3,201 to 10,000	13	80	200	4
10,001 to 35,000	20	125	315	5

\* By either touchstone or XRF

Note: For the definitions of lot and screening, see glossary in Compilation of Acts of the Standing Committee (PMC/W 1/2001).

- 4.4.1 Where an article selected for sampling is made of several parts, each part of the article shall, where practicable, be sampled.
- 4.4.2 Samples taken from separate parts of an article may be mixed if it appears that the parts are made from the same material. If the separate parts appear to be made of different materials, the samples from such parts should be assayed separately as far as possible. For articles produced by electroforming the marked standard of fineness shall not be higher than that of the lowest tested fineness.
- 4.4.3 If articles are suspected of containing an unauthorized filling, they shall be tested by drilling or cutting or by immersion in a suitable reagent. If the article is suspected of containing iron or steel, it may be tested with a magnet.
- 4.4.4 In cases where sampling may damage the article or the batch is very small (e.g. 1 or just a few articles), non-destructive testing is permissible.

## **5. Marking**

The Common Control Mark may be of a lower fineness than the national hallmark.

### **5.1 Principle**

#### **5.1.3 Marks to be applied on CCM articles**

Type 1 of the CCM is applied with the following marks:

- a) a registered responsibility mark as described in paragraph 5.4 of Annex II; and
- b) the mark of the authorised assay office.

Type 2 of the conformity CCM is applied with the following marks:

- a) a registered responsibility mark as described in paragraph 5.4 of Annex II;
- b) the mark of the authorised assay office;
- c) the fineness mark in Arabic numerals; and
- d) a chemical symbol or shield indicating the nature of the precious metal.

Marks b), c) and d) can be combined.

### **5.2 Methods of marking**

Other methods of marking: none.

### **5.3 Display**

A gold pen nib shall be considered as a separate article from the pen.

A pendant incorporating a gold or silver ingot fitted with a frame shall be considered as two separate articles, provided the ingot is loosely fitted and not permanently fixed. The frame may be accepted as a separate and complete article and marked with the Convention marks.

### **5.4 Register for responsibility marks**

-

### **5.5 The Common Control Mark**

#### **5.5.2 Approved sizes**

The minimum size (height) of the Common Control Mark and other compulsory marks for all precious metals is 0.5 mm, provided that the mark is legible by means of a 10x magnifying glass.

### **5.6 Articles consisting of more than one alloy of the same precious metal**

#### **Gold nuggets**

Native gold in the shape of nuggets is allowed -unmarked- on precious metals articles, irrespective of the standard of fineness and of criteria for the determination of colours.

### **5.7 Articles consisting of parts**

To assess whether it is practicable to apply the CCM on lesser parts, the following elements shall be considered:

- Is there a major risk that the lesser part(s) be separated permanently from the main part?
- Is it technically feasible to apply the CCM on the lesser part(s)?
- Will an additional mark have a neutral impact on the aesthetic of the piece?
- If there are large numbers of articles, is it economically viable for the Assay Office to double or triple the number of marks applied and recapture those costs by charging for it?
- In the case of lighter mass produced silver items with a lower retail value, is it reasonable to charge the customer multiple charges for multiple marks?

A “no” to any of the above elements indicates that the application of the CCM on the lesser parts may not be practicable and the additional CCM can be omitted. The final decision is the responsibility of the Assay Office.

## 5.8 Mixed precious metal articles

### 5.8.3 Exceptions

- a) White gold parts permitted on platinum articles for technical reasons:

On platinum articles, the following parts may be in white gold (750/1000):

- \* tongues, clasps and other elements of closing systems for bracelets (whether for watches or jewellery) and necklets
- \* moving parts of clips for earrings and brooches
- \* pins for brooches
- \* joints and catches for brooches

- b) A precious metal watch-case and attached bracelet may be considered as two separate articles provided that the bracelet is attached by pinning (barrette).

- c) The application of pure silver on gold articles by electro-chemical process is permitted for the technical reason of fixing mounted diamonds and enhancing the reflection of light. The application of the silver must be restricted to the internal surface of the setting only.

- d) For mixed precious metal articles, where it is not possible to apply the marks, as provided under paragraph 5.8.1 of Annex II, the following marks can be applied on the least precious metal part:

- Fineness mark of the least precious metal
- Responsibility mark
- AO mark
- CCM Type 1 (least precious metal)
- + metal symbol & fineness mark of more precious metal(s)

E.g. for a gold 750 and platinum 950 mixed precious metal article, these are: Au 750 / responsibility mark / AO mark / CCM Type 1 + Pt 950.

- e) For mixed precious metal articles, as defined paragraph 5.8.1 and 5.8.2 of Annex II, the CCM Type 2 can be applied in replacement of the CCM Type 1, provided that metal symbols clearly identify the types of precious metals.

E.g. for a gold 750 and platinum 950 mixed precious metal article, these are: Au 750 / Pt 950 / responsibility mark / AO mark / CCM Type 2.

- f) For mixed precious metal articles, where – for technical reasons – only the CCM Type 2 can be applied and where it is either not possible to identify all types of precious metals with the corresponding metal

symbols or where there is insufficient space to apply all the marks, all marks can be applied on any part of the mixed precious metal article.

## **5.9 Multimetal articles**

The precious metal part of Multimetal Articles can be marked with the mention <METAL> next to the marks defined in paragraph 5.1.2 of Annex II. The mention can be preceded by a sign e.g. + or /.

\* \* \* \* \*

## Examples of precious metals unsuitable for technical reasons

### A. General examples:

- metal wires used for the assembling of necklaces and bracelets (the metal wires must not be used as decoration);
- magnets for clasps;
- security retainers for tie tacks or badge buttons;
- screws, pins and springs, which may be hidden in the watch mechanism;
- the internal mechanism of lighters and similar mechanisms;
- blades of knives and working parts of bottle openers, corkscrews and similar articles.


### B. Examples specific for silver articles

- clasps only the tongue in a box snap;
- pins for silver badge buttons and silver brooches;
- clips for hair clasps, tie clasps, etc.;
- wire for joints of silver hinges.

### C. Examples specific to horology (clocks, watches & and similar mechanisms)

- parts of movements such as dials, crowns, winding-shafts and push-pieces;
- bars for fixing the bracelets to the wristwatches;
- screws for assembling and fixing the various elements of watch cases;
- screws for changing the length of the bracelets;
- separable tubes for winding-mechanisms on watch-cases made of gold, platinum and palladium;
- separable or inseparable tubes for winding-mechanisms on silver watch-cases;
- movement-holders and casing-rings;
- tubes and rivets for folding buckles;

- domes (double back covers of pocket-watch cases, see drawing below) under the condition that they bear the designation of their composition, for example "METAL" or "STAINLESS STEEL".



D. Pens / biros / roller-balls / propelling pencils

The following applies to writing instruments when the cap, if there is one, is detached from the body (see also drawings below).

- D1. The movements of propelling pencils (and similar mechanisms) may be of base metal.
- D2. For items with a continuous precious metal sleeve, the interior barrel may be of base metal, plastic, resin, or resin covered base metal. The inside parts in non-precious metal must not be used to reinforce the precious metal sleeve.
- D3. For items with pierced sleeves, the interior barrel may only be plastic, resin, or resin covered base metal.
- D4. Clips - may be of base metal and, if so, must be marked "METAL". They may be plated.

Note: Detachability is irrelevant.

- D5. End parts, e.g. caps, pushers - may be of base metal and, if so, must be marked 'METAL' if they are part of the interior mechanism. They may be of resin, plastic, or resin covered or plastic covered base metal.
- D6. Bands - On the barrel, when the band forms part of the closing mechanism of the cap or to assure tightness of a pen, the band may be in base metal. It may be plated. The band shall be clearly distinguishable by colour from precious metals.

Any other band, on the body or the cap is decorative and must be in precious metal.


The only exception is a clip with an integral band secured by an end cap.

- D7. Point - A base metal point is permitted provided it is a different colour. If plated, it must be marked "METAL". Resin or plastic covered base metal is permitted.


If all base metal parts are the same colour, only one part need be clearly and visibly marked 'METAL'.

Note: The intention of these consents is to define permitted visible base metal parts, and to provide a choice to manufacturers. Resin covered base metal is considered to be clearly distinguishable to the consumer as not being precious metal.

Base metal points for propelling pencils and ballpoint pens



## Base metal parts of precious metal writing instruments



### E. Diamond settings made of fine silver on 18 carat gold cufflinks




Image of a pure silver plate surrounding the stones by their crowns. An 18ct white gold elevated rehaut (yellow colour) then surrounds the circumference of the pure silver plate (grey colour).

Image of how the pure silver plate is integrated into the 18ct white gold cufflink.

\* \* \* \* \*